


3-D Printing Graphene Aerogels

A U.S. research team from Virginia Tech and the Lawrence Livermore National Lab (LLNL) has demonstrated a light-based approach for 3-D printing strong, lightweight, porous graphene aerogels—at a resolution an order of magnitude finer than other techniques. 3-D printing is well advanced for polymer foams, with some notable success, but is still an active area of research for graphene foams. Researchers have published schemes for printing 3-D graphene using a number of approaches, such as extrusion. As a result, according to the researchers, these techniques have generally printed out 3-D graphene structures with relatively weak, bending-dominated configurations, such as stacked “woodpile” structures, and relatively large achievable feature sizes (greater than 100 microns). That’s a far cry, they say, from the high-resolution, complex structures that could open up applications in areas such as energy storage and conversion.



In particular, they opted for a form of 3-D printing called projection micro-stereolithography (PμSL)—a light-based technique that allows the resin feeding the 3-D printing

process to be shaped into fine-scale, intricate forms via patterned light. Using this technique, an entire layer of 3-D-printing resin can be cured, at very fine scales, via a single UV flash. That advantage, the team reasoned, could potentially overcome some of the toolpath and sequence issues experienced by other approaches to 3-D printing of graphene. The big trick was to figure out a way to make a photocurable graphene resin—one that would quickly firm up under a light beam, but that also was sufficiently runny to be slathered layer by layer on the workpiece. To get there, Hensleigh spent some time in the chemistry lab, developing a porous graphene-oxide hydrogel with cross-linked sheets, and then using ultrasound to disperse the cross-linked graphene oxide into a dilute, 1-weight-percent suspension.

The result is exquisite, intricate, airy structures, such as lattices of octet trusses, with feature sizes on the order of 10 microns—an order of magnitude finer, according to the team, than other 3-D-printed graphene structures. They're lightweight enough to balance on a single filament of a strawberry blossom (see image at top of story). And they're also strong; as measured by their Young's modulus, the strength of the P μ SL-printed structures seems to hold up better than that of most other 3-D graphenes and other carbon aerogels as the density of the structure decreases.

For more information: doi: [10.1039/C8MH00668G](https://doi.org/10.1039/C8MH00668G)